

Series	Product	Mix Ratio	Shore Hardness	Pour Time	Demold Time @ 73°F	Total Cure Time (hr)	Cured Color	Mixed Viscosity (cP)	Specific Volume (in ³ /lb)	Specific Gravity	Linear Shrinkage (in/in)	Elongation (%)	Tensile Strength (psi)	Die B Tear Strength (pli)	Die T Tear Strength (pli)
PLATSIL® 71 and 73-SERIES (standard mold making and casting silicones)	PlatSil® 71-11	1A:1B by weight	A10	20 min.	4 hr.	24	Blue-Green	6,000	24.7	1.12	Nil	751	281	117	36
	PlatSil® 73-15	1A:1B by weight	A15	20 min.	4-5 hr.	48	White Translucent	2,500	25	1.10	Nil	640	265	55	17
	PlatSil® 73-20	1A:1B by weight	A22	5 min.	1 hr.	24	Blue Translucent	3,000	25	1.10	Nil	460	230	45	17
	PlatSil® 71-25	1A:1B by weight	A25	35 min.	16 hr.	48	Milky White	3,500	25	1.1	Nil	343	418	137	32.8
	PlatSil® 73-25	1A:1B by weight	A25	15 min.	4-5 hr.	48	Green	6,000	24.3	1.14	Nil	405	380	120	30
	PlatSil® 73-29	1A:10B by weight	A30	45 min.	16 hr.	48	White	15,000	25	1.10	Nil	531	542	90	39
	PlatSil® 71-40	1A:10B by weight	A40	90 min.	24 hr.	48	Translucent	38,000	26.6	1.04	Nil	296	438	98.6	32.9
	PlatSil® 73-40	1A:10B by weight	A40	45 min.	16 hr.	48	Yellow	15,000	25	1.10	Nil	355	465	52	7
	PlatSil® 73-45	1A:10B by weight	A45	40 min.	16 hr.	48	Green	35,000	21.3	1.30	Nil	707	631	145	62.9
	PlatSil® 71-60	1A:10B by weight	A60	30 min.	16-24 hr.	48	Magenta	55,000	22.7	1.22	Nil	220	630	80	5
PlatSil® 73-60	1A:10B by weight	A60	45 min.	16 hr.	48	Blue	40,000	21.3	1.30	Nil	202	537	113	45	
PLATSIL® FS-SERIES (fast-setting)	PlatSil® FS-10	1A:1B by weight or vol.	OO60\A13	8 min.	25 min.	24	Milky White	4,200	24.9	1.11	Nil	679	488	157.9	54.8
	PlatSil® FS-20	1A:1B by weight or vol.	OO66\A20	8 min.	25 min.	24	Milky White	3,800	24.9	1.11	Nil	626	467	148.2	52.8
PLATSIL® HTS-SERIES (high tear & tensile strength)	PlatSil® HTS-25	1A:10B by weight	A25	70 min.	24 hr.	48	Milky White	15,500	24.9	1.11	Nil	>2,000	>645	179.0	67
	PlatSil® HTS-25 Fast	1A:10B by weight	A25	15 min.	3 hr.	24	Milky White	18,000	24.9	1.11	Nil	1,706	656	176.9	73.7
	PlatSil® HTS-40	1A:10B by weight	A40	30 min.	24 hr.	48	Milky White	17,000	24.9	1.11	Nil	831	686	131.3	56.2
PLATSIL® GEL SERIES	PlatSil® Gel-OO20	1A:1B by weight or vol.	OO20	40 min.	2 hr.	24	Milky White	3,900	26	1.05	Nil	964	122	24.8	1.3
	PlatSil® Gel-OO30	1A:1B by weight or vol.	OO30	45 min.	4 hr.	24	Milky White	6,200	26	1.05	Nil	848	118	36.6	10.7
	PlatSil® Gel-OO	1A:1B by weight or vol.	OO30	6 min.	30 min.	24	Milky White	22,000	25	1.1	Nil	1,275	154	56	19
	PlatSil® Gel-10	1A:1B by weight or vol.	A10	6 min.	30 min.	24	Milky White	15,000	25	1.1	Nil	970	228	80	27
	PlatSil® Gel-25	1A:1B by weight or vol.	A25	5 min.	60 min.	24	Milky White	3,500	25	1.1	Nil	385	434	146	28
SPECIALTY	PlatSil® SiliGlass	1A:1B by weight	A40	7 min.	30 min.	24	Clear	200	28	0.97	N/A	N/A	N/A	N/A	N/A

DISCLAIMER: The information in this bulletin and otherwise provided by Polytek® is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. Before using, the user shall determine the suitability of the product for the intended use and user assumes all risk and liability whatsoever in connection therewith.

N/A = Not Applicable