

Series	Product	Mix Ratio	Shore Hardness	Pour Time	Demold Time @ 73°F	Cured Color	Mixed Viscosity (cP)	Specific Volume (in ³ /lb)	Specific Gravity	Elongation (%)	Tensile Strength (psi)	Die C Tear Strength (pli)
POLY 74-SERIES Soft to Medium-Hard Polyurethane Rubbers	Poly 74-20	1A:2B by weight	A20	20 min.	16 hr.	Yellow	800	27.5	1.01	1,060	217	43
	Poly 74-24	1A:1B by weight	A25	20 min.	16 hr.	Amber	2,000	27.5	1.01	750	220	55
	Poly 74-29	1A:1B by weight	A30	30 min.	16 hr.	Black or Off-White	2,800	27.5	1.02	1,600	520	109
	Poly 74-30	1A:1B by weight	A30	25-30 min.	16 hr.	Amber/Varies	2,000	27.5	1.01	506	281	62
	Poly 74-30 Clear	1A:1B by weight	A30	25-30 min.	16 hr.	Transparent Amber	2,000	27.5	1.01	507	281	62
	Poly 74-30 HT	1A:1B by weight	A30	25-30 min.	16 hr.	Amber/Varies	2,000	27.5	1.01	975	304	70
	Poly 74-40	2A:1B by weight	A40	20 min.	16 hr.	Varies	3,400	27.5	1.01	400	349	95
	Poly 74-41	1A:1B by weight	A40	20 min.	16 hr.	Amber/Varies	2,000	27.5	1.01	1,060	360	77
	Poly 74-44	2A:1B by weight	A45	20 min.	16 hr.	Gray	3,500	27.5	1.01	2,422	462	129
	Poly 74-45	1A:1B by weight	A45	30 min.	16 hr.	Yellow	2,000	27.5	1.02	1,135	408	82
	Poly 74-55	4A:1B by weight	A55	15 min.	16 hr.	Amber	4,000	27.5	1.01	894	679	155
POLY 75-SERIES Medium to Hard Polyurethane Rubbers	Poly 75-59	1A:1B by weight	A60	10 min.	16 hr.	Amber	2,500	27	1.05	588	637	122
	Poly 75-60	1A:1B by weight	A60	10 min.	16 hr.	Amber	1,200	27	1.05	459	545	103
	Poly 75-65	1A:1B by weight	A65	35 min.	16 hr.	Yellow	3,000	27	1.04	550	520	145
	Poly 75-70	1A:1B by weight	A70	40 min.	16 hr.	Gray	3,000	27	1.05	724	938	299
	Poly 75-75	2A:1B by weight	A75	20 min.	16 hr.	Amber	4,000	26	1.06	722	1,064	247
	Poly 75-79	2A:1B by weight	A80	20 min.	16 hr.	Yellow	2,000	26	1.07	369	655	143
	Poly 75-80	2A:1B by weight	A80	45 min.	16 hr.	Yellow	5,000	26	1.07	468	750	199
POLY 81-SERIES Very Hard Rubbers	Poly 81-90	100A:40B by weight	A90	23 min.	16 hr.	Varies	2,000	26.6	1.06	463	1,550	357
	Poly 81-D45	100A:20B by weight	D45	19 min.	16 hr.	Varies	1,600	26.4	1.08	327	1,426	380
POLY GEL® SERIES Brushable & Sprayable Rubbers	Polygel® 35	1A:1B by weight or volume	A35	10-15 min.	16 hr.	Light Blue	Medium Thixotropic	27.5	1.02	620	436	70
	Polygel® Spray 35	1A:1B by weight or volume	A35	10 min.	16 hr.	Light Blue (varies)	Medium Thixotropic	27.5	1.06	627	507	71
	Polygel® Spray 50	1A:1B by weight or volume	A50	5-7 min.	16 hr.	Green	Medium Thixotropic	27.5	1.07	885	834	117
FORMRUB SERIES	FormRub 35	1A:1B by weight	A35	15 min.	16 hr.	Turquoise	600	27.2	1.02	2,250	283	69
	FormRub 50	1A:1B by weight	A50	15 min.	16 hr.	Orange	800	26.6	1.03	975	600	115
	FormRub 60	1A:1B by weight	A60	22 min.	16 hr.	Off-White/Tan	2,000	26.6	1.04	850	835	189
	FormRub 65	1A:1B by weight	A65	35 min.	16 hr.	Yellow/Amber	1,500	26.6	1.04	600	500	150
PT FLEX SERIES Fast-Setting Rubbers	PT Flex 20	1A:1B by weight	A20	4 min.	2 hr.	Tan	520	27.5	1.0	770	250	50
	PT Flex 50	1A:1B by weight	A50	5 min.	2 hr.	Yellow/Amber	450	26.9	1.03	200	250	50
	PT Flex 60	1A:1B by weight	A60	5 min.	2 hr.	Yellow/Amber	600	26.9	1.03	235	345	70
	PT Flex 70	1A:1B by weight	A70	4 min.	2 hr.	Yellow/Amber	700	26.4	1.05	175	730	130
	PT Flex 85	1A:1B by weight	A85	5 min.	2 hr.	Yellow/Amber	750	26.2	1.06	250	1,064	190
	PT Flex D60	2A:1B by weight	D60	10 min.	16 hr.	Amber	3,000	26.9	1.03	130	3,140	790
SPECIALTY	Poly GlassRub 50	1A:1B by weight or volume	A50	30 min.	16 hr.	Glass-Like/Blue-Clear	1,200	27.5	1.0	750	360	74
	Poly 47-105 <i>Superior dimensional stability for casting veneer stone panel systems/large pavers</i>	1A:1B by weight	A40	20 min.	16 hr.	Off-White	4,000	27.5	1.01	864	541	76

DISCLAIMER: The information in this bulletin and otherwise provided by Polytek® is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. Before using, the user shall determine the suitability of the product for the intended use and user assumes all risk and liability whatsoever in connection therewith.