

Series	Product	Mix Ratio	Shore Hardness	Pour Time	Demold Time @ 73°F	Cured Color	Mixed Viscosity (cP)	Specific Volume (in ³ /lb)	Specific Gravity	Shrinkage upon cure (%)	Elongation (%)	Tensile Strength (psi)	Die B Tear Strength (pli)	Die T Tear Strength (pli)
TINSIL® 70-SERIES	TinSil® 70-11	1A:10B by weight	A10	45 min.	16 hr.	Blue	10,000	25.5	1.08	~0.3	600	221	89	24
	TinSil® 70-20	1A:10B by weight	A20	60 min.	16 hr.	Blue	10,000	25.3	1.1	~0.3	830	363	100	31
	TinSil® 70-25	1A:10B by weight	A25	60 min.	16 hr.	Blue	14,000	25.3	1.1	~0.3	516	306	107	36
	TinSil® 70-60 <small>(use to cast low-melt metals up to ~600°F)</small>	5A:100B by weight	A60	30 min.	24 hr.	Red	17,000	18	1.5	~0.8	134	262	25	ND
TINSIL® 80-SERIES	TinSil® 80-15	1A:10B by weight	A15	30 min.	24 hr.	Peach	12,000	25.3	1.1	~0.2	503	249	87	31
	TinSil® 80-30	1A:10B by weight	A30	45 min.	24 hr.	Peach	17,000	23.7	1.17	~0.2	383	392	145	43
	TinSil® 80-40	1A:10B by weight	A40	45 min.	24 hr.	Peach	20,000	22.9	1.21	~0.2	244	400	62	17
SPECIALTY	TinSil® Gel-10	1A:10B by weight	A10	45 min.	16 hr.	Translucent	10,000	25.3	1.1	~0.3	654	221	89	24
	TinSil® Brush/Spray 25	1A:10B by weight	A25	30 min.	16 hr.	Translucent	Thixotropic	25.3	1.1	~0.3	608	278	75	27

DISCLAIMER: The information in this bulletin and otherwise provided by Polytek® is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. Before using, the user shall determine the suitability of the product for the intended use and user assumes all risk and liability whatsoever in connection therewith.

ND = Not Determined