

Series	Product	Mix Ratio by Volume	Mix Ratio by Weight	Shore Hardness	Pot Life (1-lb mix)	Demold Time* @ 73°F unless otherwise noted	Cured Color	Mixed Viscosity (cP)	Specific Volume (in ³ /lb)	Specific Gravity	Linear Shrinkage (in/in)	Elongation (%)	Max Exotherm (°F)	Heat Deflection Temp. (°F)	Tensile Strength (psi)	Elastic Modulus (psi)	Flexural Modulus (psi)	Flexural Strength, 5% Strain (psi)
EASYFLO SERIES Fast-Setting, Low-Viscosity Polyurethane Resins	EasyFlo 60	1A:1B	100A:90B	D65	2-2.5 min.	15-30 min.	White	60	26.9	1.03	0.0041	13.9	230	149	2,936	72,627	93,112	3,915
	EasyFlo 90	1A:1B	100A:90B	D70	5 min.	60-120 min.	White	200	26.1	1.06	<0.001	5.1	175	164	4,387	134,685	157,356	6,125
	EasyFlo 120	1A:1B	100A:90B	D65	2-2.5 min.	15-30 min.	Off-White	120	26.9	1.03	0.0065	10.3	200	146	3,534	85,149	133,765	4,845
	EasyFlo Black	1A:1B	1A:1B	D70	1.5-2 min.	10-15 min.	Black	200	26.4	1.05	0.008	6.3	245	197	3,835	76,056	120,904	5,521
	EasyFlo Clear	1A:1B	100A:85B	D72	2-2.5 min.	15-30 min.	Amber	110	25.5	1.08	0.0154	7.7	208	133	4,091	97,532	165,733	6,007
	EasyFlo 100 FR	1A:1B	1A:1B	D65	2-2.5 min.	15-30 min.	Off-White/Tan	120	25.2	1.10	0.0065	9	200	165	3,170	85,928	117,878	4,284
	EasyFlo Spray FR	1A:1B	100A:90B	D75	N/A (Spray)	5-10 min.	Off-White	250	23.9	1.16	ND	8.3	251	175	7,110	165,600	280,007	10,545
POLY 15-SERIES High-Strength Resins	Poly 15-3	N/A	1A:1B	D80	15 min.	12-16 hr.	Tan	2,000	18	1.53	0.0006	2.6	125	ND	3,509	202,276	479,648	5,232
	Poly 15-3X	N/A	1A:1B	D80	5 min.	1-12 hr.	Tan	2,000	18	1.53	0.0015	2.6	160	149	3,890	ND	ND	ND
	Poly 1511	N/A	1A:1B	D71	10 min.	1-16 hr.	White	400	25.1	1.10	0.0044	5.4	251	142	6,712	118,352	241,223	10,046
	Poly 1512	N/A	1A:1B	D71	22 min.	1-16 hr.	White	400	25.1	1.10	0.0034	5.4	251	142	6,712	118,352	241,223	10,046
	Poly 1512X	N/A	1A:1B	D71	5 min.	0.5-4 hr.	White	400	25.1	1.10	0.0048	5.4	251	142	6,712	118,352	241,223	10,046
KAST-SERIES High-Performance Tooling Resins	BC-8002 Kwik-Kast	1A:1B	1A:1B	D85	5-6 min.	1-2 hr.	Gray	2,350	15	1.8-1.9	0.0008	ND	ND	179	4,900	ND	ND	6,700
	BC-8655 Kwik-Kast	1A:1B	1A:1B	D83	8-10 min.	1-2 hr.	Blue	2,120	14.6	1.9	0.0008	ND	ND	177	4,120	ND	ND	6,250
	BC-8009 Slo-Kast	1A:1B	1A:1B	D85	14-18 min.	3-4 hr.	Gray	2,250	15	1.8-1.9	0.0002	ND	ND	173	5,850	ND	ND	6,900
	BC-8010 Metal-Kast	1A:1B	1A:1B	D83	6-7 min.	1.5-2 hr.	Gray	2,250	15.4	1.8	0.0007	ND	ND	179	4,046	ND	ND	6,650
POLY-OPTIC® 14-SERIES Water-Clear Resins	Poly-Optic 1410	N/A	3A:2B	D80	15 min.	2 hr. (1" thick)	Water Clear	700	25.8	1.07	ND	27	265	100	4,566	96,830	144,158	4,893
	Poly-Optic 1411	1A:1B	100A:90B	D80	9 min.	30 min. (0.5" thick)	Water Clear	600	25.8	1.07	0.0018	7	228	138	6,083	133,956	250,992	8,478
	Poly-Optic 1412	1A:1B	1A:1B	D80	8 min.	30 min. @ 175°F	Water Clear	750	25.8	1.07	0.0019	11.1	235	227	9,825	179,886	295,101	12,261
	Poly-Optic 1420	N/A	2A:1B	D85	15 min.	8 hr @ 150°F 30 min. @ 175°F	Water Clear	250	26.3	1.05	ND	5.3	311	168	7,900	171,500	250,000	12,600
	Poly-Optic 14-70	N/A	4A:5B	A70	15 min.	24-48 hr.	Water Clear	340	26.1	1.06	0.0016	234	190	N/A	564	N/A	N/A	N/A
POLY-OPTIC® 17-SERIES Mercury Free Water-Clear Resins	Poly-Optic 1730X	1A:1B	1A:1B	D80	8 min.	1 hr	Water Clear	450	28.8	1.04	0.0015	6.7	235	137	5,670	104,000	213,000	7,920
	Poly-Optic 1730	1A:1B	1A:1B	D80	15 min.	1 hr.	Water Clear	400	28.8	1.04	0.0015	7.4	235	137	5,480	112,000	201,000	7,350
	Poly-Optic 1740	1A:1B	1A:1B	D70	14 min.	1 hr.	Water Clear	400	28.5	1.03	0.0015	12	210	137	3,180	80,100	91,000	3,560
SPECIALTY	Poly Plasti-Flex (FLEXIBLE RESIN)	N/A	35A:100B	A90	3 min.	15 min.	Tan	3,000	34	0.81	ND	81	190	N/A	1,330	29,450	N/A	N/A
	Poly LiteCast (LIGHTWEIGHT PLASTIC)	N/A	1A:1B	D55	5 min.	0.5 - 4 hr.	Tan	2,480	35	0.78	ND	3	251	ND	2,398	105,470	16,630	4,402

DISCLAIMER: The information in this bulletin and otherwise provided by Polytek® is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. Before using, the user shall determine the suitability of the product for the intended use and user assumes all risk and liability whatsoever in connection therewith.

*Demold time varies with thickness of casting and the amount of accelerator used. ^Poly-Optic 1490 must be pressure cast or used with vacuum casting equipment (not degassing).

ND = Not Determined | N/A = Not Applicable